




ATLANTA


METALLURGICAL SERVICES

Gat No. 194, Hanuman nagar, Shiye, MIDC Shiroli, Kolhapur. 416 122
Cell: +91-9309225144

Web : www.atlantametalab.com
Email : atlantametalab@gmail.com

- Metallurgical Testing
- Failure Analysis
- Heat Treat Process Analysis
- Material Solutions
- Metallurgical Consulting

TEST REPORT - Salt Spray (Fog Chamber) Test			
Name of Customer : CORROCONTROL PACKSYS PVT.LTD Plot No-C-2,MIDC,GokulShirgaon,Kolhapur Kolhapur (Maharashtra, India)		Report No. : SS-19720/23-24/1 Date of Receipt : 27/02/2024 Date of Test : 07/03/2024 Date of Report : 07/03/2024	
Lab ID : 19720/23-24		Customer Reference : DC No-1113 / Date-25.02.2024	
Identification of Sample : Spacer Mouting 662-01 (Marvelous Eng)		Heat No. :	
Material Specification : ---		Condition of Sample : Salt Spray Test Piece	
Type of Test Description : Salt Spray (Fog Chamber) Test		Test Method : ASTM-B-117-19	
Instruments Utilized : Digital Rh Indicator with Sensor		Calibration Date : 15/07/2023 & Due On 14/07/2024	
Test Carried Out at : Permanent Facility			
TEST DETAILS			
Job Log In Date & Time : 27/02/2024 11:00AM		Job Log out Date & Time : 07/03/2024 11:00AM	
Exposure Time (Hours) : 216.00			
TEST PARAMETERS			
pH : 7.2	Salt Spray Solution : 5 % Nacl		
R Humidity : 95 %	Temperature (°C) : 35°C		
TEST RESULT			
After 24 Hours	No rust observed.		
After 48 Hours	No rust observed.		
After 72 Hours	No rust observed.		
After 96 Hours	No rust observed.		
After 120 Hours	No rust observed.		
After 144 Hours	No rust observed.		
After 168 Hours	No rust observed.		
After 192 Hours	No rust observed.		
After 216 Hours	No rust observed.		
Tested By  Mr. Chandrakant N. Sawardekar (Lab Assistant)		 ATLANTA METALLURGICAL SERVICES KOLHAPUR	
		Authorized Signatory  Mr. Amol S. Turambekar (Quality Manager)	
Terms & Conditions : 1. The results relate only to the sample tested, Sample(s) drawn by party. 2. Test Certificate shall not be re-produced except in full without the written approval of Laboratory. 3. AMS has made their best endeavors to provide accurate and reliable information. AMS is not responsible for any financial liability due to any act of omission or error made 4. Samples are preserved for 15 Days. Any ambiguity in test results should be brought forward to the Lab Management within this period.			



ATLANTA

METALLURGICAL SERVICES

Gat No. 194, Hanuman nagar, Shiye, MIDC Shirol, Kolhapur. 416 122
Cell: +91-9309225144

Web : www.atlantametalab.com
Email : atlantametalab@gmail.com


- Metallurgical Testing
- Failure Analysis
- Heat Treat Process Analysis
- Material Solutions
- Metallurgical Consulting

TEST REPORT - Salt Spray (Fog Chamber) Test


Name of Customer : CORROCONTROL PACKSYS PVT.LTD Plot No-C-2, MIDC, Gokul Shirgaon, Kolhapur Kolhapur (Maharashtra, India)	Report No. : SS-19720/23-24/1 Date of Receipt : 27/02/2024 Date of Test : 07/03/2024 Date of Report : 07/03/2024
--	---

Lab ID : 19720/23-24
Customer Reference : DC No-1113 / Date-25.02.2024
Identification of Sample : Spacer Mouting 662-01 (Marvelous Eng)
Heat No. :
Material Specification : ---
Condition of Sample : Salt Spray Test Piece
Type of Test Description : Salt Spray (Fog Chamber) Test
Test Method : ASTM-B-117-19
Instruments Utilized : Digital Rh Indicator with Sensor
Calibration Date : 15/07/2023 & Due On 14/07/2024
Test Carried Out at : Permanent Facility

TEST DETAILS



Before



After 216 Hrs

Observation : No Rust Observed after 216 Hrs

Tested By

Mr. Chandrakant N. Sawardekar
(Lab Assistant)



Authorized Signatory

Mr. Amol S. Turambekar
(Quality Manager)

Terms & Conditions :

1. The results relate only to the sample tested, Sample(s) drawn by party.
2. Test Certificate shall not be re-produced except in full without the written approval of Laboratory.
3. AMS has made their best endeavors to provide accurate and reliable information. AMS is not responsible for any financial liability due to any act of omission or error made
4. Samples are preserved for 15 Days. Any ambiguity in test results should be brought forward to the Lab Management within this period.